Product information

Gear Oil (GL4) SAE 85W-90



Description

Mineral based transmission oil provides accurate function at any temperature even during high torque loads. Consistent viscosity quarantees a strong lubricating film for maximum wear protection. Enables easy shifting and smooth gear engagement.

Properties

- high pressure-absorption capability
- reduces running noise
- does not attack common sealing materials
- excellent viscosity/temperature properties
- minimizes wear
- high resistance to aging

Specifications and approvals:

API GL4 • MIL-L 2105 • ZF TE-ML 16A • ZF TE-ML 17A • ZF TE-ML 19A • ZF approval number ZF002054

LIQUI MOLY also recommends this product for vehicles or assemblies for which the following specifications or original part numbers are required:

MAN 341 Typ E1 • MAN 341 Typ Z2

Technical data

SAE class (gear oils) 85W-90 **SAE J306**

Density at 59 °F 0,885 g/cm³

DIN 51757

Viscosity at 104 °F 197 mm²/s

ASTM D 7042-04

Viscosity at 212°F 17.6 mm²/s

ASTM D 7042-04

Viscosity at 10 °F <150000 mPas

DIN 51398

Viscosity at 10 °F (Brook-

field)

<= 150000 mPas ASTM 2983-09

Viscosity index

DIN ISO 2909

Flash point 428 °F

DIN ISO 2592

5°F Pour point

DIN ISO 3016

Foaming behavior at 75 °F 0/0 ml

ISO 6247

Foaming behavior at 75 °F 0/0 ml after 200 °F ISO 6247

Foaming behavior at 200 $0/0 \, \text{ml}$

ISO 6247

Technical data

Neutralization number 0,8 mg KOH/g

DIN 51558 T1

Saponification number 2,0 mg K0H/g

DIN 51559 T1

Oxide ash $0.01 \, \text{g} / 100 \, \text{g}$

DIN EN ISO 6245

Sulfate ash 0,02 g/100g

DIN 51575

Color number (ASTM) L 3.5

DIN ISO 2049

Areas of application

Universal use in gearboxes, hypoid axles and differentials without an integrated differential lock system (wet clutch) where a gear oil meeting current specifications is required or recommended.

Application

Observe the manufacturers instructions!

Available pack sizes

1 l Can plastic 20016

USA AND CANADA (-EN-

Our information is based on thorough research and may be considered reliable, although not legally binding.



Phone: +49 (0)731/1420-0 Fax: +49 (0)731/1420-82 e-mail: info@liqui-moly.de Service-hotline: 0800/8323230 Technical hotline: +49 (0)731/1420-871

www.liqui-moly.de